

KingFill[®] C250

High performance, non-sanded cementitious tile grout for joints up to 3 mm

TECHNICAL PROPERTIES @ 23 ± 2°C. W/P = 0.34

DESCRIPTION

KingFill C250 is a non-sanded high performance tile grout specially designed for grouting narrow joints up to 3 mm in all types of tile and stone on walls and floors.

KingFill C250 is a unique blend of cement, fine grained inert materials, and special additives that forms when mixed with water a smooth tile grout ideally suitable for filling narrow joints between tiles to provide a dense, hard, and durable tile joints with excellent abrasion resistance and reduced water absorption characteristics.

KingFill C250 is available in wide range of brilliant colours that provide a uniform and aesthetic joint appearance.

APPLICATIONS

- ☐ Specially designed for fine grouting of joints up to 3 mm.
- ☐ Excellent performance in high traffic areas such as shopping centers, hospitals and universities.
- ☐ Superb performance in wet areas and submerged conditions such as swimming pools and fountains.
- ☐ Non-sag, suitable for wall applications.
- ☐ Excellent for internal and external applications.

ADVANTAGES

- ☐ Specially designed for fine grouting of joints up to 3 mm.
- ☐ Excellent performance in high traffic areas such as shopping centers, hospitals and universities.
- ☐ Superb performance in wet areas and submerged conditions such as swimming pools and fountains.
- ☐ Non-sag, suitable for wall applications.
- ☐ Excellent for internal and external applications.

Fresh wet density:	1.8 ± 0.1 g/cm ³
Compressive strength: ISO 13007-4,4.1.4 ANSI A118.6,4.5	> 15 MPa @ 28 days > 21 MPa @ 28 days
Flexural strength: ISO 13007-4,4.1.3 ANSI A118.6,4.7	> 2.5 MPa @ 28 days > 2.8 MPa @ 28 days
Tensile strength: ANSI A118.6,4.6	> 2.4 MPa @ 28 days
Working time:	60 min
Shrinkage: ISO13007-4,4.3	< 3.0 mm
Abrasion resistance: ISO 13007-4,4.4	< 1000 mm ³
Water absorption: ISO 13007-4,4.2	< 5 g @ 240 min
VOC: ASTM D2369	< 10 g/ltr (complies with LEED)

LIMITATIONS

Do not use for:

- ☐ Joint widths exceed 3 mm.
- ☐ Grouting tiles in industrial floors where high chemical resistance is required.
- ☐ Cases where a rapid utilization of surfaces is required.
- ☐ Filling expansion, contraction or construction joints in walls and floors, these joints should be filled with a suitable flexible sealant from the KINGKRETE range.

STANDARDS

Kingfill C250 complies with the following standards:

- ☐ ISO 13007-3 and BS EN 13888 as an improved cementitious grout with additional characteristics of reduced water absorption and high abrasion resistance (CG2AW).
- ☐ ANSI A118.6 as a standard cementitious grout.

METHOD OF USE

KingFill[®] C250

Substrate preparation

Before grouting, ensure that the adhesive has completely dried and hardened. Adhesive should be left for 24 hours before applying the grout, unless rapid setting adhesive is used.

All tiles and joints must be clean and free from oil, grease or loose materials.

Remove the tile spacers and ensure that the grout joints are uniform and their widths do not exceed 3 mm to avoid slumping.

Mixing

To ensure proper mixing, a mechanically powered mixer or drill fitted with suitable paddle should be used.

1.65 - 1.75 litres of clean fresh water for each 5 kg bag (water/powder ratio of 0.33 - 0.35 by weight) should be added to a clean container. The powder is then added slowly to the water while mixing continuously at low speed (400 - 600 rpm).

Mixing time should be continued for 3 minutes until a uniform consistency and free of lumps mixture is obtained. Allow a slake time for 5 minutes, then remix for additional 1 minute without adding any more water.

Important:

⚠ Adding too much water will weaken the joints, cause surface discoloration, and promote the formation of cracks, always follow the mentioned mixing ratio.

⚠ Using appropriate spatula or rubber float, fill with pressure the joints completely with Kingfill C250.

⚠ Immediately, remove the excess grout by moving the spatula or the edge of the rubber float diagonally to the tiles.

⚠ When the grout starts to set (usually 20 - 30 minutes at normal conditions), use a damp sponge in a circular motion to remove the excess grout and level the joints.

⚠ After drying, clean the tiles surface using a dry cloth.

It is recommended to remove grout from the tile surfaces before full setting of the grout. Failure to do so may result in difficulty in removing any remains and makes it necessary to use a mechanical means in cleaning, which may scratch the tile surfaces.

YIELD

The approximate yield of grout can be calculated as per the following equation:

$$\text{Yield (m}^2\text{/kg)} = \frac{6}{WD (0.02 + 1/L+1/H)}$$

Where;

L: Tile length (cm)

H: Tile width (cm)

D: Average joint depth (mm)

W: Average joint width (mm)

Note: Grout yield subject to ±15% tolerance.

PACKAGING

Kingfill C250 is available in 5 kg bags.

CLEANING

All tools should be cleaned immediately after use with fresh clean water. Hardened materials should be cleaned mechanically.



KingFill[®] C250

Shelf life is 1 year when stored under cover, out of direct sunlight and protected from extremes of temperature.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult KingKrete's Technical Services Department.

HEALTH AND SAFETY

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Reseal containers after use. Use in well ventilated areas and avoid inhalation.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local KingKrete representative.

KingKrete Inc. reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All products originating from KingKrete's manufacturing facilities are manufactured under a management system independently certified to conform to the requirements of the quality standard ISO 9001.

* Properties listed are based on laboratory-controlled tests.

® = Registered trademark of the KingKrete-Group in many countries.

KK-ME-06.2-FI-C250-R3-2601

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this KingKrete Inc. publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by KingKrete Inc. either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not KingKrete Inc. are responsible for carrying out procedures appropriate to a specific application.

KingKrete Middle East
www.kingkrete.com

Disclaimer: the IAS mark relates to certified management system and not to the product mentioned on this datasheet





KINGKRETE[®]
We Create Future

KingFill[®] C250
