

KingAdd[®] 300RP

Retarding and water reducing admixture.

DESCRIPTION

KingAdd 300RP is formulated from selected polymers specially designed to enable the water content of the concrete to perform more effectively. This effect can be used to improve workability, to increase ultimate strengths or to facilitate a reduction in the cement content while sustaining mix properties.

KingAdd 300RP has retarding property, this effect can be used overcome transportation delay problems and where long setting time is required.

APPLICATIONS

- ☐ Long concrete deliveries.
- ☐ Hot weather concreting.
- ☐ Where high workability retention and retardation are required.
- ☐ To produce high quality concrete of improved durability and water tightness.
- ☐ To improve cohesion in concrete mixes.

ADVANTAGES

- ☐ Improved workability, reduces placing and compaction problems.
- ☐ Cold joints can be avoided by extending initial and final concrete setting time.
- ☐ Higher strength with same cement content.
- ☐ Cement saving without affecting strength.
- ☐ More durable concrete as a result of reduction in permeability and lower water to cement ratio.

COMPATIBILITY

KingAdd 300RP can be used with all types of Portland cement and cement replacement materials.

KingAdd 300RP is compatible with other KINGKRETE admixtures used in the same concrete mix. If more than one type of admixture is to be used in concrete mix, they must be dispensed to the concrete separately.

STANDARDS

KingAdd 300RP complies with ASTM C494 Type B & D and with BS 5075 Part 1.

TECHNICAL PROPERTIES @ 25°C:

Colour:	Brown liquid
Freezing point:	-2°C
Specific gravity:	1.21 - 0.05
Chloride content: BS5075	Nil
Air entrainment:	Typically less than 2% additional air is entrained above control mix at normal dosages

METHOD OF USE

KingAdd 300RP should be added to the concrete with the mixing water to achieve optimum performance. Automatic dispenser should be used to dispense the correct quantity of KingAdd 300RP to the concrete mix.

DOSAGE

The guidance dosage of KingAdd 300RP is 0.30 to 0.70 liter per 100kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Representative trials should be conducted to determine the optimum dosage of KingAdd 300RP to meet the performance requirements by using the materials and conditions in actual use.

EFFECTS OF OVER DOSAGE

Overdosing of KingAdd 300RP will cause the following:

- ☐ Significant increase in retardation.
- ☐ Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

SETTING TIME

Although the setting time is dependent on the dosage of KingAdd 300RP, the following factors should be considered:

- ☐ Retardation is increased with lower levels of tri-calcium in the cement.
- ☐ Lower temperatures will delay the setting time.
- ☐ SRC cement gives higher retardation level than ordinary cement.
- ☐ Using more than one type of admixture in the same concrete mix could affect the setting time.
- ☐ Retardation level is increased when cement replacement materials are used in the concrete mix.

CLEANING

KingAdd 300RP can be washed with fresh cold water.



KingAdd® 300RP

PACKAGING

KingAdd 300RP is available in 25 liters pails, 210 liters drums and 1000 liters bulks supply.

STORAGE

Shelf life is 1 year when stored under cover, out of direct sunlight and protected from extremes of temperature.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult KingKrete's Technical Services Department.

HEALTH AND SAFETY

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Reseal containers after use. Use in well ventilated areas and avoid inhalation.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local KingKrete representative.

KingKrete Inc. reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All products originating from KingKrete's manufacturing facilities are manufactured under a management system independently certified to conform to the requirements of the quality standard ISO 9001.

* Properties listed are based on laboratory-controlled tests.

® = Registered trademark of the KingKrete-Group in many countries.

AD-300RP-R3-2601

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this KingKrete Inc. publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by KingKrete Inc. either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not KingKrete Inc. are responsible for carrying out procedures appropriate to a specific application.

KingKrete North America
www.kingkrete.com

Disclaimer: the IAS mark relates to certified management system and not to the product mentioned on this datasheet

