

# KingGrout<sup>®</sup> RE5

Epoxy resin cartridge system for anchoring.

## DESCRIPTION

KingGrout RE5 is a two component high strength pure epoxy resin anchoring grout pre-packed in dual cartridge system with fast curing rate.

KingGrout RE5 is formulated for permanent installation of steel reinforcement bars and threaded rods into concrete substrates in structural applications.

## APPLICATIONS

KingGrout RE5 is ideally designed for use in the following applications:

- 🔧 Permanent installation of reinforcement starter bars and dowel bars.
- 🔧 Permanent installation of hand rails, safety fence, wall ties, railway tracks and ground anchors.

## ADVANTAGES

- 🔧 Exceptional rapid strength development.
- 🔧 Resistant to dynamic loading.
- 🔧 Exceptional high compressive.
- 🔧 Extremely dense.
- 🔧 Exceptional bond to concrete and steel surfaces.
- 🔧 Suitable for dry and damp concrete holes.
- 🔧 Good chemical resistance.
- 🔧 High ultimate and early strengths.

## STANDARDS

KingGrout RE5 evaluated in accordance with the EOTA TR023 "Assessment of post-installed rebars connections".

- 🔧 KingGrout RE5 when tested at normal temperature complies with the requirements of ASTM C881, Types I, II\*, IV and V\*, Grade 3, Class C.

\*Except for gel time.

## METHOD OF USE

### Substrate preparation

Substrate should be sound, clean and free from grease or any contamination. Bars should be free from any loose rust deposits. Holes can be drilled using a hammer drill to produce a rough surface or by coring to produce a smooth surface. KingGrout RE5 bond strength will be the same in both cases.

## TECHNICAL PROPERTIES

Colour:	Red
Bond strength: ASTM C882-99	≥ 10 MPa @ 2 days ≥ 13.5 MPa @ 14 days
Compressive yield strength: ASTM D695-02a	≥ 70 MPa @ 7 days
Linear coefficient of shrinkage on cure: ASTM D2566-86	< 0.005 @ 7 days
Compressive modulus: ASTM D695	≥ 1400 MPa @ 7 days
Elongation at break: ASTM D638-03	> 1.5% @ 7 days
Water absorption: ASTM D570-98	< 1%

Deformed or ribbed bars will give a higher performance than smooth or other bar types. After drilling, holes should be brushed and blown out twice, to remove all drilling debris.

### Application

- 🔧 Unscrew the protective cap, remove the insert plug and attach the static mixing nozzle.
- 🔧 Insert the cartridge into the cartridge gun and dispense sufficient material until an even colour is achieved.
- 🔧 Usually 10 ml of extruded material should be adequate.
- 🔧 Insert the nozzle into the base of the hole, apply pressure to the gun and slowly withdraw the nozzle as the hole fills.
- 🔧 Normally, it is enough to fill the hole approximately two- third full.
- 🔧 Insert the stud/steel bar into the hole with a twisting action, ensuring that is fully embedded.
- 🔧 Allow the resin to cure fully before loading.
- 🔧 When filling holes overhead or in porous block work, the use of plastic sleeves is recommended.

Partly used cartridge are reusable, Remove the static mixer and surplus base and catalyst components from the cartridge nozzle, insert the plug and screw on the protective cap.

## WORKING AND CURING TIMES

# KingGrout® RE5

Resin Cartridge Temperature	Base Material Temperature	Working Time	Curing Time
35 to 40°C	35 to 40°C	8 min	4 hr
25 to 30°C	25 to 30°C	13 min	10 hr
20 to 25°C	20 to 25°C	25 min	12 hr
10 to 15°C	10 to 15°C	100 min	24 hr
10 to 15°C	5 to 10°C	120 min	45 hr

*Always ensure that the cartridge temperature is > 10°C prior to using it.*

**TABLE I**

Bar diameter (mm)	Hole diameter (mm)	Embedded length (mm)	Bar area (mm <sup>2</sup> )	Maximum pull out force (kN)*	Needed quantity of KingGrout RE5 per hole (ml)
10	12	110	79	36	8.3
12	14	130	113	51	13.3
14	16	150	154	69	20.1
16	20	180	201	94	37.7
18	24	200	254	117	60.3
20	26	230	314	150	81.4
25	31	280	491	228	140.9
32	40	360	804	376	301.6

\* Maximum pull-out force that yield a concrete splitting failure pattern.

## DESIGN CONSIDERATION

Table I summarizes the forces that each deformed steel reinforcement bar can withstand at each specified holes depth.

These forces were calculated in accordance with EOTA TR023 "Assessment of post-installed rebars connection", considering that the yield strength of the steel is 420 MPa and the compressive strength of concrete is 25 MPa cube.

## ESTIMATING

The required quantity of KingGrout RE5 depends on the hole diameter and depth. Normally, it is enough to fill the hole two-third full. The estimated volume of KingGrout RE5 can be calculated using the following equation:

$$\text{Volume (ml)} = (\pi/6000) \cdot \Phi_h^2 \cdot H_D$$

Where:

$\Phi_h$ : Hole diameter (mm).

$H_D$ : Hole depth (mm).

## CLEANING

All tools should be cleaned immediately after finishing by KINGKRETE Solvent. Hardened materials can be cleaned mechanically.

## PACKAGING

KingGrout RE5 is available in 400 ml twin cartridge system.

## STORAGE

Shelf life is 1 year when stored under cover, out of direct sunlight and protected from extremes of temperature.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult KingKrete's Technical Services Department.

## HEALTH AND SAFETY



# KingGrout® RE5

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Reseal containers after use. Use in well ventilated areas and avoid inhalation.

## NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local KingKrete representative. KingKrete Inc. reserves the right to have the true cause of any difficulty determined by accepted test methods.

## QUALITY AND CARE

All products originating from KingKrete's manufacturing facilities are manufactured under a management system independently certified to conform to the requirements of the quality standard ISO 9001.

\* Properties listed are based on laboratory-controlled tests.

® = Registered trademark of the KingKrete-Group in many countries.

## K KK-NA-07.4-GR-RE5-R3-2601

### STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this KingKrete Inc. publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

### NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by KingKrete Inc. either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not KingKrete Inc. are responsible for carrying out procedures appropriate to a specific application.

KingKrete North America  
www.kingkrete.com

**Disclaimer:** the IAS mark relates to certified management system and not to the product mentioned on this datasheet

