

KingFloor[®] C300T

Trowel applied cementitious screed.

DESCRIPTION

KingFloor C300T is a pre-bagged trowel applied cementitious screed for use as a leveling mortar and heavy duty base underlayment. The product consists of well graded sand particles, a blend of cements, additive and fibers to ensure ease of use and produce consistent quality screed.

APPLICATIONS

KingFloor C300T is formulated for use as a basic screed and trowel applied levelling mortar for applications such as:

- 🔧 Floor leveling prior to tiling works.
- 🔧 Repair of breakage caused by mechanical and electrical fittings installations or maintenance.
- 🔧 Repair of damaged plaster.
- 🔧 Topping over heated flooring conduits.
- 🔧 Can be installed over hard wood, metal surfaces as a base layer.

ADVANTAGES

- 🔧 Pre-mixed and only requires the addition of water.
- 🔧 Elimination of manual labor quality problems resulting from onsite screed proportioning.
- 🔧 Saves storage space of screed mixing raw materials (sand, cement).
- 🔧 Reducing dust and material loss resulting from open storage of screed raw materials.
- 🔧 Cost effective, easy to apply.
- 🔧 Smooth finish.

STANDARDS

KingFloor C300T complies with EN 13813, Class CT-C60-F10.

METHOD OF USE

Substrate preparation

Concrete substrates should be fully cured and achieve a minimum compressive strength of 25 N/mm² and a minimum pull-off strength of 1.5 N/mm². The concrete substrate should be below 75% RH and have less than 4% moisture content. Alternatively, KingFloor DPM should be applied according to the priming section.

TECHNICAL PROPERTIES @ 25°C

Colour:	Cement grey
Compressive strength: EN13892-2	≥ 40 MPa @ 7 days ≥ 60 Mpa @ 28 days
Flexural strength: EN 13892-2	≥ 8 MPa @ 28 days
Fresh wet density:	2.2 ± 0.1 g/cm ³
Working time:	30 - 40 min @ 25°C
Maximum grain size:	3 mm
Application thickness:	10 - 50 mm
Setting time:	
Initial	45 - 60 minutes
Final	16 hours
Drying shrinkage: ASTM C490	< 500 microns @ 28 days

Surface preparation

Concrete surfaces must be degreased using degreasing products, torching or any other suitable method which assures the surface is free from any oil traces.

Surfaces should be sound and with no irregularities as they can affect the finish of the applied product.

Concrete surfaces are to be mechanically prepared to remove laitance and achieve a flat surface, grit blasting or surface profiling equipment are preferred. Acid etching can be used after consulting with KINGKRETE's Technical Department.

Surface defects such as voids and blowholes should be repaired before application. Consult KINGKRETE's Technical Department for the best repair material.

Surfaces must be free of any dust or loose particles before product application. Use suitable methods like vacuuming or sweeping.

If possible, apply the product on a small test area before actual application to check for any problems with the surface preparation.

MIXING

Mix the contents of the bag with 5.0 - 5.5 litre for 50 kg bag and 2.5 - 2.75 litre for 25 kg bag of fresh clean water using a drum or free fall mixer for 3 - 5 minutes prior to spreading.



KingFloor[®] C300T

PRIMING

It is not usually necessary to prime absorbent surfaces. However, to ensure satisfactory bonding, the prepared surface should be dampened down to minimize pin holing. Ensure that the surface is in a saturated surface dry condition i.e. no visible surface water prior to application of KingFloor C300T.

For surfaces with RH between 75% and 85%, without the need to dampen the surface, prime with one coat of KingFloor DPM and allow to dry prior to application of KingFloor Primer.

For surfaces with RH greater than 86%, without the need to dampen the surface, prime with two coats of KingFloor DPM and allow the second coat to dry prior to the application of KingFloor Primer.

After KingFloor DPM has been applied and left to cure, apply KingFloor Primer and whilst it is still tacky fully blind with Anti-slip Aggregate #2 at approximately 3 kg per m², until the surface is covered and no resin spots remain. Allow to dry fully overnight and remove excess aggregate before applying KingFloor C300T.

APPLICATIONS

The mixed mortar shall be spread evenly by trowel and tamped well in place with wooden float at a thickness of 10 - 50 mm in single application. Greater thickness can be achieved by application of multiple layers. KingFloor C300T shall be finished with steel trowel to achieve the required smoothness and to fully close the surface.

COVERAGE

- 1.25 m² per 25 kg bag @ 10 mm thickness.
- 2.50 m² per 50 kg bag @ 10 mm thickness.

PACKAGING

KingFloor C300T is available in 25 and 50 kg bags.

CLEANING

All tools should be cleaned immediately after finishing by water.

STORAGE

Shelf life is 1 year when stored under cover, out of direct sunlight and protected from extremes of temperature.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult KingKrete's Technical Services Department.

HEALTH AND SAFETY

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Reseal containers after use. Use in well ventilated areas and avoid inhalation.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local KingKrete representative.

KingKrete Inc. reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE



KingFloor® C300T

All products originating from KingKrete's manufacturing facilities are manufactured under a management system independently certified to conform to the requirements of the quality standard ISO 9001.

* Properties listed are based on laboratory-controlled tests.

® = Registered trademark of the KingKrete-Group in many countries.

K KK-SA-05.1-FL-C300T.-R3-2601

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this KingKrete Inc. publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by KingKrete Inc. either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not KingKrete Inc. are responsible for carrying out procedures appropriate to a specific application.

KingKrete South America
www.kingkrete.com

Disclaimer: the IAS mark relates to certified management system and not to the product mentioned on this datasheet

