

KingGrout[®] MC100

Block and brick premixed laying mortar.

DESCRIPTION

KingGrout MC100 is a polymer modified, ready to use interior and exterior block adhesive specially designed for use with blocks and bricks.

KingGrout MC100 is composed of a blend of cement, sand, limestone, dry powder additives and selected polymers which when mixed with water produces a thixotropic mortar suitable for fixing all types of blocks and bricks, and to be used on the block walls for filling gaps.

APPLICATIONS

- ☐ For permanent fixing of all types of blocks and bricks.
- ☐ Can be used internally and externally.

ADVANTAGES

- ☐ Water resistant, will not be affected in wet areas.
- ☐ Low permeability to water.
- ☐ Ready for use, just requires the addition of water.
- ☐ Non sag, good consistency.
- ☐ High bond strength.
- ☐ Suitable for internal and external application.
- ☐ Shrinkage controlled, polymer modified cementitious mortar.
- ☐ Complies with the LEED requirements for VOC.

STANDARDS

KingGrout MC100 complies with the requirements of ASTM C387, C1714, C270 Type S, N and O.

METHOD OF USE

Blocks Condition

All used blocks must be checked to be clean and free from oil or any loose materials. It is recommended to wet the used blocks before the application of the adhesive, especially in hot and dry conditions.

Mixing

To ensure proper mixing, a mechanically powered mixer or drill fitted with suitable paddle should be used.

3.0 - 3.5 litres (for each 25 kg bags) of clean water should be added to clean container.

TECHNICAL PROPERTIES @ 25°C. W/P = 0.13:

Appearance:	Grey cement based powder
Fresh wet density (mixed):	2.0 ± 0.1 g/cm ³
Skin over time:	8 mins. @ 20 mm thickness
Pot life:	1 - 2 hr
Compressive strength: ASTM C109/109M-02	> 14 MPa @ 28 days
Flexural strength: BS6319, Part 3:1990	≥ 2.0 MPa @ 28 days
Maximum aggregate size:	3.0 mm
Initial setting:	2 - 3 hr
Temperature limitations:	Below 5°C & above 38°C

The powder is then added slowly to the water while mixing continuously with low speed mixer/drill (400 - 600 rpm). Mixing time should be continued for 3 minutes until a uniform consistency is obtained.

Application

- ☐ Spread to a uniform thickness of 15 - 25 mm using a trowel.
- ☐ Place blocks firmly over the applied area.

CURING

The applied areas should be protected from direct sunlight and heavy wind. Curing with water is needed for at least 2 - 3 days after setting.

CLEANING

All tools should be cleaned immediately after finishing by water.

PACKAGING

KingGrout MC100 is available in 25 and 50 kg bags.

YIELD

Approximately 14 litres per 25 kg bag.

STORAGE

Shelf life is 1 year when stored under cover, out of direct sunlight and protected from extremes of



KingGrout[®] MC100

temperature.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult KingKrete's Technical Services Department.

HEALTH AND SAFETY

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Reseal containers after use. Use in well ventilated areas and avoid inhalation.

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local KingKrete representative. KingKrete Inc. reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All products originating from KingKrete's manufacturing facilities are manufactured under a management system independently certified to conform to the requirements of the quality standard ISO 9001.

* Properties listed are based on laboratory-controlled tests.

® = Registered trademark of the KingKrete-Group in many countries.

NOTE

KK-SAS-07.4-GR-MC100-R3-2601

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this KingKrete Inc. publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

K

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by KingKrete Inc. either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not KingKrete Inc. are responsible for carrying out procedures appropriate to a specific application.

