

KingInsulate® C100

Cementitious adhesive base coat plaster for external wall insulating systems with improved

bond strength.

DESCRIPTION

KingInsulate C100 is a cementitious adhesive specially designed to be used for permanent fixing of thermal insulation boards to a wide range of substrates including concrete and masonry.

APPLICATIONS

- ☒ For permanent fixing of expanded polystyrene boards.
- ☒ For permanent fixing of extruded polystyrene boards.
- ☒ For permanent fixing of mineral wool boards.

ADVANTAGES

- ☒ Easy to apply.
- ☒ Water resistant.
- ☒ Non sag.
- ☒ Very good compressive strength.
- ☒ Very good bond strength.
- ☒ Requires no primer.

METHOD OF USE

Substrate Preparation

All surfaces must be clean and free from oil, grease or loose materials. Substrate should be dimensionally stable. Allow time for shrinkage and structural strain movements.

PRIMING

KingInsulate C100 can be applied directly on concrete, cement plaster and masonry. In case of very porous substrates, water can be sprayed on the surface prior to the application.

MIXING

To ensure proper mixing, a mechanically powered mixer or drill fitted with suitable paddle should be used.

6.25 - 6.75 litres (for each 25 kg bags) of clean water should be added to clean container. The powder is then added slowly to the water while mixing continuously with low speed mixer/drill (400 - 600 rpm). Mixing time should be continued for 3 minutes until a uniform consistency is obtained.

APPLICATION

Apply the mortar in a strip around the insulation board with a few spots in the middle. In case of a smooth base material, a toothed trowel can be used to spread the mortar on the back of the insulation board.

TECHNICAL PROPERTIES

Colour:	Grey
Fresh wet density: (mixed)	1.7 ± 0.1 g/cm ³
Open time:	10 min @ 3 mm thickness
Pot life:	6 - 8 hr
Compressive strength: EN 1015-11	≥ 8.0 MPa @ 28 days
Adhesion strength with concrete substrate: EN 1015-12	≥ 1.0 MPa
Adhesion strength with EPS boards: EN 13494	≥ 100 KPa @ 28 days
Coefficient of water absorption by capillary-C: EN 1015-18	≤ 0.1 kg/m ² .min0.5
Thermal conductivity coefficient: EN 1745, A12	0.9 W/m.K

CLEANING

All tools should be cleaned immediately after use with fresh clean water. Hardened materials should be cleaned mechanically.

PACKAGING

KingInsulate C100 is available in 25 kg bags.

YIELD

Approximately 6 m²/25 kg bag at 3 mm thickness.

STORAGE

Shelf life is 1 year when stored under cover, out of direct sunlight and protected from extremes of temperature. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult KingKrete's Technical Services Department.

HEALTH AND SAFETY

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Reseal containers after use. Use in well ventilated areas and avoid inhalation.



KingInsulate® C100

Cementitious adhesive base coat plaster for external wall insulating systems with improved

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local KingKrete representative. KingKrete Inc. reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All products originating from KingKrete's Middle East facility are manufactured under a management system independently certified to conform to the requirements of the quality standards ISO 9001, ISO 14001 and ISO 45001.

* Properties listed are based on laboratory-controlled tests.
® = Registered trademark of the KingKrete-Group in many countries.

Ref: KK-10042-MEA-R01 | Issue: 01.2026

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this KingKrete Inc. publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by KingKrete Inc. either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not KingKrete Inc. are responsible for carrying out procedures appropriate to a specific application.

KingKrete Middle East
Qatar – Syria
www.kingkrete.com

Disclaimer: the IAS mark relates to certified management system and not to the product mentioned on this datasheet

